



Modelling of Smart Materials



Bishakh Bhattacharya and Nachiketa Tiwari

Department of Mechanical Engineering

Indian Institute of Technology, Kanpur



LECTURE 10

Modelling of Induced Strain Actuation (Part 1)

Topics Covered in the Last two Lectures:

- Constitutive Relationship of Piezoelectric Material
- Simplified Equations for Piezo-patch
- Piezoelectric Constants
- Different Piezoelectric Materials and their properties
- Piezo-actuators – various displacement and force measurement techniques

Organization of this Lecture


- Induced Strain Actuation (ISA) – Uniform Strain Model
- Static Equilibrium Configuration against Uniform Strain
- Configuration against Bending Strain

Motivation

- Vibration and Shape Control of Flexible Structures and Compliant joints demand development of strain/mechanical force inside such systems.
- Hence, it is important to study how piezoelectric patches would behave while integrated to such systems.
- This is the motivation of modelling induced strain actuation of flexible structures.
- The smart patches could be either surface-bonded or embedded inside the structure.

Induced Strain Actuation – Uniform Strain Model

- Static model was developed by Crawley and Anderson
- Assumed that the strain remains constant across the piezo-patch while it varies linearly inside the substructure.



Induced Strain Actuation – Uniform Strain Model

- The model has been used for surface bonded actuation.
- Actuators embedded/ bonded on top and bottom of the beam are excitable in the same phase to cause uniform extension or contraction.
- Bending also can be generated through out-of-phase excitation of the piezo-ceramics

Static equilibrium corresponding to the induced strain can be expressed as

$$2 F_a + F_s = F_i ,$$

F_a is the reactive force developed in each active layer, F_s is that in the substrate, and F_i is the total force.

Equilibrium equation in terms of Strain

$$2(E_p S_a A_p) + E_s S_s A_s = 2\Lambda E_p A_p$$


where S denotes the strain, E the modulus of elasticity, A the area of cross-section and Λ the free strain.

The subscript p denotes the piezoelectric material and s denotes the substrate.

It is assumed that near the actuator-substrate interface, the strain remains unchanged, hence, we can write

$$S_a = S_s = \frac{2\Lambda}{2 + \Psi_e}$$


where, the in-plane stiffness ratio ψ_e is $(E_s A_s) / (E_p A_p)$.




For bending, considering equilibrium of active and reactive moments one gets

$$E_p S_a A_p t_s + \frac{2E_s I_s S_a}{t_s} = \Lambda E_p A_p t_s$$

$$S_a = S_s = \frac{6\Lambda}{6 + \psi_b} \quad \text{with the bending stiffness ratio } \psi_b = 12 (EI)_s / [t_s^2 (EA)_p].$$





When the thickness of the bonding layer is finite, the presence of visco-elastic bonding material reduces the transmission of stress from actuator to substrate and the induced strain to actuation strain ratio is shown to be given by the following relationships

$$S_a = \frac{\alpha}{\alpha + \psi} \Lambda \left[1 + \frac{\psi \cosh(\Gamma \bar{x})}{\alpha \cosh(\Gamma)} \right]$$

Strain in the Host Substrate will be

$$S_s = \frac{\alpha}{\alpha + \psi} \Lambda \left[1 - \frac{\cosh(\Gamma \bar{x})}{\alpha \cosh(\Gamma)} \right]$$

$$\Gamma^2 = \bar{D} \frac{\alpha + \psi}{\psi}, \quad \bar{D} = \frac{(G / E_a)(t_b / t_p)}{(t_b / l_p)^2}$$

Γ is the non-dimensional length parameter varying from -1 to $+1$ (edge to edge of the actuator).

Geometric constant α is 2 for extension and 6 for bending; ψ is the stiffness ratio related to bending or extension based on the appropriate case. G is the shear modulus of the bonding layer and Γ is the shear lag contributed by the bonding layer of thickness t_b

References

- Crawley, E. F., Intelligent Structures for Aerospace: a technology overview and assessment, AIAA, 33 (8), 1994, pp. 1689-1699

END OF LECTURE 10